

Page 1 of 2



Floctan 2

>>> Tannic Acid Floctan 2

Product data-sheet



Floctan 2 is a blended high molecular weight hydrolysable tannic acid specially purified for textile applications. This high purity grade was specially developed for electrostatic flock activation.

Floctan 2 is a 100 % natural material extracted from renewable plant materials using dedicated strictly controlled production facilities. No preservatives or additives are used in the production of Floctan 2.

PROPERTIES(*)

light yellow granular powder, free of visible impurities Appearance: slight in solution, typical tannic acid. Odour:

Purity (on dry material): min. 95 % Moisture: max. 7.0 % Density: $0.30 - 0.45 \text{ g/cm}^3$ Ash content: max. 0.3 % pH (1 % in water): 3 - 4Colour Gardner (1:10; alcohol): max. 6 Solubility in H₂O: clear Staining test: pass (1) Only selected data is represented here, for a full set of specifications we refer to our **Specifications** sheet.

Floctan 2 is a general-purpose grade used in applications such as upholstery, garments, etc...on all kinds of colour shades, ranging from off-white to dark colours. It insures long lasting flock activation.

USAGE >>>

Typical Floctan 2 dosage levels are 1-2 % owf. Exact dosage levels are dependant on the end application, titter of the fibre and type and depth of the colour. For more detailed information regarding flock activation we refer to the specific Application Fact Sheets on this subject.

To prevent local over-dosage Floctan 2 is best added as a 5-10 % solution. Due to its granular form Floctan 2 easily dissolves in cold, or even better in hot water (e.g. 60°C). Clear solutions up to 50 % (m/V) can be prepared, but are highly viscous.

As the tannic acid concentration increases shelf life of these solutions increases: 1 % (w/v) solutions should be used within the same day, 5-10 % solutions can be stored for 1 week at room temperature, and 30 % solutions can be used for several months, assuming no micro-biological contamination has occurred.





Page 2 of 2

Maximum Floctan 2 uptake on Polyamide 6.6 is achieved at pH = 3-3.5. pH can be adjusted with acetic acid; if water with high levels of alkaline is used formic acid is sometimes required. Tartaric acid can be used to improve yellowing stability. Floctan 2 should not be used in alkaline conditions.

High concentrations of dissolved iron or copper will cause the formations of respectively dark blue or brown tannic acid-metal complexes, and should therefore be avoided. Even small amounts of iron in the ppm range will already cause a marked coloration of the treatment liquors. This discoloration does not negatively influence electrostatic properties of the flock but can lead to a darkening of the colour.

We advice against the use of metal chelating agents in the flock activation bath to remedy excessive amounts of dissolved iron because these agents can interfere with the normal flock activation process.

>>> STORAGE AND HANDLING

Floctan 2 does not require special storage conditions and has a shelf life of min. 5 years if stored in a dry area in its original closed packaging. It is not frost sensitive and normal ambient temperatures (i.e. 5-25°C) suffice.

Prolonged exposure of Floctan 2 to light can cause a gradual colour shift. This does not influence technical performance of the product unless colour is a critical parameter in the application. Storage of Floctan 2 open to the atmosphere can result in moisture uptake from the surroundings. Therefore reseal the inner plastic bag and keep the lid on the fibre drum if Floctan 2 is not in use.

Due to its granular form Floctan 2 produces little or no dust during handling.

>>> PACKAGING

Floctan 2 is a spray-dried granular product available in 25 kg fibre drums lined with an inner polyethylene bag.

>>> FURTHER INFORMATION

Further safety information is provided in our **Material Safety Data Sheet**.

Upon simple request a controlled copy of our Specifications can be provided by our QC-department.

Information on usage and applications can be found in our **Application Fact Sheets.** Our R&D department can provide you further detailed information on composition and regulatory status.

Deliveries are accompanied by a Certificate of Analysis.

CAS Nr.: 1401-55-4 EINECS/ELINCS: 215-753-2

The information provided in this product data sheet is based on the present state of our knowledge. Some of the applications mentioned in this document are protected by patent law. Ajinomoto OmniChem nv/sa cannot be held responsible for patent law infringements and the customer should contact the patent holder if so required. Due to the many process parameters involved we are not able to submit a general recommendation. It only shows without liability on our part the uses to which our products can be put. However, Ajinomoto OmniChem nv/sa cannot be held responsible for the consequences of the application of the above described product.